

FABRENE®

INDUSTRIAL SYNTHETIC FABRICS

TYPE FABRENE UDL®

Made from a polypropylene nonwoven, coated on two sides with polyethylene.

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	g/m ²		151	ASTM D3776
Tensile Grab Strength	Newton	Warp	466	ASTM D751
		Weft	351	
Tear Strength * (tongue)	Newton	Warp	41	ASTM D2261
		Weft	37	
Tear Strength (trapezoid)	Newton	Warp	107	ASTM D4533
		Weft	72	
Coating	µm	Grey	31.5	ASTM D1777 MOD
	µm	Grey	32.8	
Mullen Burst Strength	kPa		813.61	ASTM D751
Vapour Perneance	Perms		.79	ASTM E-96 Proc. A
Fastener Pull Resistance	Newton	Unaged	134	ASTM D3462
Nominal Thickness	µm		458	ASTM D1777 MOD

* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene UDL® contains some ultraviolet inhibitors and is suitable for short-term outdoor applications.
For further information, contact your FABRENE Inc. representative.

Suggested Applications: nonpermeable roofing membrane.

SALES INQUIRIES

Fabrene Inc.
Tel: (888) 322-7363 ext 234
Tel: (705) 476-7057 ext 234
Fax: (705) 476-7787

ORDER DESK

North Bay, ON, Canada
Tel: (888) FABRENE
(888) 322-7363
ext. 222 or 226
Fax: (705) 476-0665

MAILING ADDRESS

Fabrene Inc.
240 Dupont Rd.
P.O. Box 4040
North Bay, ON, Canada
P1B 9B4

Date: 07/07/06

